

ACP 5080P

Industry leading flatness and tolerances combined with excellent dimensional stability.

High precision low stress aluminium cast plate, ACP 5080P, is precision surface machined on both sides to industry leading precise tolerance standards. Fine grain structure, low porosity and excellent machining characteristics all define the cost saving and value-added attributes of ACP 5080P. Superb industry leading material dimensional stability is inherent in every plate of ACP 5080P; thanks to proprietary processes and manufacturing control, our flatness and tolerances are industry leading, predictable, and precise. Each plate is inspected and protected on both sides finally.

alimex[®]
PRECISION IN ALUMINIUM

ACP 5080P

INDUSTRY LEADING FLATNESS AND TOLERANCES COMBINED
WITH EXCELLENT DIMENSIONAL STABILITY

Chemical Composition

EN AW-5083 (AlMg4.5Mn0.7), acc. to DIN EN 573-3/3.3547

Material Properties

Machinability	very good (HSC/HPC excellent)
Weldability (TIG, MIG)	good (with S Al 5183)
Anodising Properties	good, not decorative
Polishing	very good
Corrosion Resistance	very good
Eroding Properties	good

Typical Mechanical Properties for standard sizes

Tensile Strength R_m	240 - 290 MPa (N/mm ²)
0.2 % Yield Strength R_p 0.2	110 - 130 MPa (N/mm ²)
Elongation A	15 (+/- 5) %
Brinell Hardness	74 (+/- 5) HB

Typical Physical Properties

Density	2.66 g/cm ³
Thermal Conductivity	110 - 140 W/(mK)
Electrical Conductivity	16 - 19 MS/m (m/Ω mm ²)
Modulus of Elasticity	~70,000 N/mm ²
Coefficient of Thermal Expansion	24.2 * 10 ⁻⁶ /K

Standard Sizes

Thickness	5 - 220 mm
Width	1520 - 2160 mm
Length	3020 - 4050 mm

Tolerances for standard sizes

Surface Finish R_a	≤ 0.25 μm
Tolerance in Thickness	+/- 0.1 mm
Flatness	≤ 8 mm thickness ≤ 0.2 mm
	> 8 - 12 mm thickness ≤ 0.15 mm
	> 12 - 220 mm thickness ≤ 0.13 mm
	(Linear measured section 1 m)
Tolerance in Width for Plates	0/+10 mm
Tolerance in Length for Plates	0/+10 mm

Tolerance (L/W) for cut pieces:

≤ 150 mm thickness	DIN ISO 2768-m
> 150 mm thickness	0/+3 mm

Other tolerances on request.

alimex GmbH Precision in Aluminium

Karl-Arnold-Straße 14 - 16 | 47877 Willich | Germany
Phone: +49 (0) 2154 9177 0
Email: contact@alimex.de | www.alimex.de

alimex ACP Shanghai (China)

612A, Tower 1 German Centre
No. 88 Keyuan Road, ZhangJiang Hi-Tech Park
Pudong New District, Shanghai
201203, China

alimex ACP Asia Sdn Bhd

Block 1 no. 7, Jalan SiLC 1/4, Kawasan Perindustrian SiLC
Iskandar Puteri 79200, Johor Malaysia
Phone: +60 (7) 553 9827
Email: info@alimex.com.my | www.alimex.com.my

alimex Precision in Aluminum, Inc. (alimex Americas)

195 Shop Grove Drive - Unit A, Columbia, SC 29209 USA
Phone: +1 (803) 339-0757
Email: sales@alimexamericas.com | www.alimexamericas.com